

Casting compound

Wepuran VU 4452/41 SV-HF

The casting compound **Wepuran VU 4452/41 SV-HF** protects and insulates electronic components from extreme climatic influences and aggressive media as well as from mechanical attack.

- Base: polyurethane resin (UR)
- solvent-free/VOC free
- temperature range from -65 to at least +120 °C [-85 up to at least 248 °F]
- good adhesion on almost all materials
- high mechanical strength
- good resistance to water, moisture, lyes, acids, and numerous chemicals
- **UL Recognised Component: best flame class V-0 acc. to UL 94,**
UL File No. E99285
- complies with hazard level 3 of the railway standard EN 45545-2:2013 due to the oxygen index (OI) of 51 % in acc. with ISO 4589-2:2006 (2.8 mm layer thickness)

Characteristics

Colour/ appearance		blue
Viscosity* at 20 °C [68 °F] DIN EN ISO 3219	component A hardener (component B) mixture	5000 ± 500 mPas 130 ± 30 mPas 2500 ± 500 mPas
Density at 20 °C [68 °F] DIN EN ISO 2811-1	component A hardener (component B) mixture	1.51 ± 0.05 g/cm ³ 1.21 ± 0.05 g/cm ³ 1.45 ± 0.05 g/cm ³
Pot life of mixture at 19–21 °C [66.2-69.8 °F] in acc. with DIN EN 14022, approx. 200 mL Double viscosity Tenfold viscosity		≈ 45 min ≈ 90 min

* measured with Haake RS 600, C 35/1°, D = 100 s⁻¹,
viscosity measuring unit supplied by Thermo Fisher Scientific, www.thermofisher.com

Indices: VU = casting compound opaque, /41 = mixing ratio 4 : 1,
SV = self-extinguishing, HF = halogen-free

Physical and mechanical properties

These properties are reached after 14 days storage at room temperature (18-23°C [64.4-73.4°F]).

Property	Test method	Result
Shore-D hardness	DIN ISO 7619-1	65-75
Water absorption	DIN EN ISO 62 (30 min 100 °C / 15 min 23 °C [30 min 212 °F / 15 min 73.5 °F])	≈ 1 %
Glass transition temperature Tg	TMA	≈ 20 °C [68 °F]
Coefficient of thermal expansion CTE	TMA	≈ 50 ppm/°C < Tg ≈ 150 ppm/°C > Tg
Temperature shocks*	in accordance with IPC-TM-650, 2.6.7.1, -65 to +125 °C [- 85 to 257 °F]	passed
Thermal class*	Based on DIN IEC 60 085	E = 120 °C [248 °F]
Temperature index (TI)*	in accordance with DIN EN 60216 (IEC 60216), revised 2001 Mass loss: 5 % 10 % 20 % 50 %	after 5000 / 20000 h ≥ 110 °C/ 90 °C ≥ 125 °C/ 105 °C ≥ 135 °C/ 115 °C ≥ 150 °C/ 125 °C

* can be used in a temperature range of **-60 up to at least + 120 °C** [-76 up to at least 248 °F]. Both at the lower and upper ends of this range the performance and reliability of the material can be negatively affected in some applications. In these cases, additional pre-trials and tests are required.

Electrical properties

These properties are reached after 14 days storage at room temperature (18-23°C [64.4-73.4 °F]).

Property	Test method	Result
Dielectric strength	VDE 0303, part 21 DIN EN 60243-1	≥ 38 kV/mm
Surface resistance	VDE 0303, part 30 DIN IEC 60093	≥ 1.5 x 10 ¹² Ohm
Specific volume resistivity	VDE 0303, part 30 DIN IEC 60093	≥ 2.6 x 10 ¹⁵ Ohm x cm
Comparative tracking index (CTI, tracking resistance)	DIN EN 60112	CTI > 600*

Processing



Please read this technical report and the publications listed below carefully before using the product. These sheets are enclosed with the first shipment of product or sample.

MSDS

The corresponding material safety data sheet contains detailed information and characteristics on safety precautions, environmental protection, transport, storage, handling and waste disposal.

TI

[Technical information TI 15/2](#) "Selection criteria and processing instructions for casting compounds"

TI

[Technical information TI 15/3](#) "Protective measures when using chemicals including lacquers, casting compounds, thinners, cleaning agents"

TI

[Technical information TI 15/10](#) "Processing of 2-pack systems"

Since the many different permutations make it impossible to evaluate the whole spectrum (parameters, reactions with materials used, chemical processes and machines) of processes and subsequent processes in all their variations, the parameters we recommend are to be viewed as guidelines only that were determined in laboratory conditions. We advise you to determine the exact process limitations within your production environment, in particular as regards compatibility with your specific follow-up processes, in order to ensure a stable fabrication process and products of the highest possible quality.

The specified product data is based upon standard processing conditions/test conditions of the mentioned norms and must be verified if necessary while observing suitable test conditions on processed products.

Feel free to contact our application technology department (ATD) if you have any questions or for a consultation.

Safety recommendations

- When using chemicals, the common precautions should be carefully noted.
- Ensure that the equipment used is in compliance with the requirements laid down in the material safety data sheet.



Wear protective gloves and safety goggles!
Avoid skin contact!
Ensure sufficient technical ventilation in the workplace.
Observe standard work hygiene measures (wash hands etc.).

CAUTION: The labels on our containers indicate both the volume [L] and weight [kg]. The mixing ratio applies to the weight.
 Version 07/2021

Mixing



Stir before use



Component A : hardener (component B) = 4 : 1 (parts by weight)

Auxiliary products recommended

- ELPESPEC® [sealing mastic EH 13.271](#)
 solvent-free paste for sealing jobs in electronics and electrical engineering, self-adhesive and permelastec
- ELPESPEC® [adhesion promoters EH 13.950](#)
 for improving the adhesion; it is applied thinly to the parts that will come into contact with the casting compound
- ELPESPEC® [mould release agent EH 13.650](#)
 solvent-, silicone- and grease-free, for pre-treating the surfaces of parts to be potted; after curing, the potting can be easily removed from the mould without residue
- ELPESPEC® [cleaning agent R 13.780](#)
 for the cleaning of work place and tools; cleaning should be effected immediately after processing as cleaning becomes increasingly difficult the further the curing process progresses and is impossible after final curing

Drying/Curing

The following specifications for a quantity of 25 g serve as a guideline:

	Room temperature (18-23 °C [64.4-73.4 °F])	80 °C [176 °F]
Cured	14 days	2.5 h

Packaging

The packing units available are indicated in our offer which we will send you upon request.

Shelf life and storage conditions



Shelf life: In sealed original containers at least 4 months



Storage conditions: +5 °C to +25 °C [+41 °F to +77 °F]



Protect against humidity



Protect hardener (component B) against frost

For warehousing reasons, isolated cases may occur where the shelf life upon shipment is less than the shelf life indicated in this technical report. However, it is ensured that our products have **at least** two-thirds of their shelf life remaining when they leave our company. Labels on containers show shelf life and storage conditions.

Disclaimer

All descriptions and images of our goods and products contained in our technical literature, catalogues, flyers, circular letters, advertisements, price lists, websites, data sheets and brochures, and in particular the information given in this literature are non-binding unless expressly stated otherwise in the Agreement. This shall also include the property rights of third parties if applicable.

The products are exclusively intended for the applications indicated in the corresponding technical data sheets. The advisory service does not exempt you from performing your own assessments, in particular as regards their suitability for the applications intended. The application, use and processing of our products and of the products manufactured by you based on the advice given by our Application Technology Department are beyond our control and thus entirely your responsibility. The sale of our products is effected in accordance with our current terms of sale and delivery.

Any questions? We would be pleased to offer you advice and assistance in solving your problems. Samples and technical literature are available upon request.

Lackwerke Peters GmbH & Co. KG
Hooghe Weg 13, 47906 Kempen, Germany

Internet: www.peters.de
E-Mail: peters@peters.de

Phone +49 2152 2009-0
Fax +49 2152 2009-70

peters
Coating Innovations
for Electronics