

# ELPEGUARD® thick film coatings of the series UV-LED Twin-Cure® DSL 1602 FLZ

The **ELPEGUARD®** thick film coatings of the series **UV-LED Twin-Cure® DSL 1602 FLZ** are used to protect and insulate electronic assemblies so that they can fulfil higher requirements regarding reliability and service life. Owing to their very good resistance against moisture and condensation an excellent protection against corrosion (such as electro corrosion and migration) is possible even under harsh climatic conditions.

- basis: copolymer of polyurethane (UR) and polyacrylate (AR)
- solvent-free
- UV LED curing at a wavelength of 395 nm, or UV curing in common UV curing units
- UV-LED Twin-Cure® DSL 1602 FLZ/400: tested by Trace Laboratories-East according to **IPC-CC-830C**
- powerful protection through electrical insulation properties directly after UV curing
- chemical cross-linking reaction in shadow zones
- excellent mechanical and chemical resistance
- UV-LED Twin-Cure® DSL 1602 FLZ/400: UL Recognised Component: best flame class V-0 acc. to **UL 94** (UL file no. E80315)
- compliant with China standard **GB 30981-2020**
- temperature range of -65 to +130 °C [-85 to 266 °F]
- depending on the coating thickness also suitable for coating flexible circuits (“flex-to-install”, bend stress during assembly only)
- excellent edge coverage, wetting and underfilling of components (“micro-casting”), very good capillar-active behaviour, yet not suitable as underfill material for BGA’s
- excellent adhesion
- when applied in thick layers, components may be fixed to protect against vibration
- can be mechanically stripped for repair purposes (blasting method)
- possibility of touch-up and repair coatings as well as double coating

## Characteristics

	<b>DSL 1602 FLZ/75</b>	<b>DSL 1602 FLZ/400</b>
Colour/ appearance	colourless, fluorescent	colourless, fluorescent
Solids content	100 %	100 %
Viscosity* at 20 °C [68 °F], DIN EN ISO 3219	75 ± 25 mPas	400 ± 100 mPas
Density at 20 °C [68 °F], DIN EN ISO 2811-1	1.00 ± 0.05 g/cm <sup>3</sup>	1.06 ± 0.05 g/cm <sup>3</sup>

\* measured with Haake RS 600, C 35/1°, D = 100 s<sup>-1</sup>  
 viscosity measuring unit supplied by Thermo Fisher Scientific, [www.thermofisher.com](http://www.thermofisher.com)

Indices: UV = UV curing, LED = for LED technology, DSL = thick film coating, FLZ = fluorescent, /400 = viscosity of 400 mPas, /75 = viscosity of 75 mPas

## Physical and mechanical properties

These values are achieved after UV LED curing and 14 days' storage at room temperature.

<b>Property</b>	<b>Test method</b>	<b>DSL 1602 FLZ/400</b>	<b>DSL 1602 FLZ/75</b>
Thermal shock resistance	IPC-CC-830C, 3.7.2 -65 to +125 °C [-85 to 257 °F]	passed* (coating thickness ≤ 100 µm)	passed* (coating thickness ≤ 100 µm)
	1000 cycles -40 °C [-40 °F] to +125 °C [257 °F]. dwell time 30 min transfer time < 10 s	no cracks or delamination	no cracks or delamination
Adhesion	IPC-TM-650, 2.4.28.1	passed	passed
Flexibility	IPC-CC-830C, 3.5.5	passed	passed
Glass transition temperature Tg	TMA	≈ 40 °C [104 °F]	≈ 0 °C [32 °F]
Coefficient of thermal expansion (CTE)	TMA	≈ 140 ppm/°C < Tg ≈ 275 ppm/°C > Tg	≈ 165 ppm/°C < Tg ≈ 270 ppm/°C > Tg

## Electrical properties

These values are achieved after UV LED curing and 14 days' storage at room temperature.

<b>Property</b>	<b>Test method</b>	<b>DSL 1602 FLZ/400</b>	<b>DSL 1602 FLZ/75</b>
Dielectric strength	IPC-TM-650, 2.5.6.1	≥ 50 kV/mm	≥ 40 kV/mm
	IPC-CC-830C, 3.6.1	passed	passed
Specific volume resistivity	DIN EN 62631-3-1	≥ 1.0 x 10 <sup>14</sup> Ohm x cm	≥ 1.0 x 10 <sup>14</sup> Ohm x cm
Surface resistance	DIN EN 62631-3-2	≥ 1 x 10 <sup>14</sup> Ohm	≥ 1 x 10 <sup>13</sup> Ohm
Moisture and insulation resistance	IPC-CC-830C, 3.7.1 (65 °C [149 °F]/90 % r.h.)	passed	passed
	85/85 test (3 d, 85 °C [185 °F], 85 % R.H.)	≥ 3.0 x 10 <sup>8</sup> Ohm	≥ 1.0 x 10 <sup>8</sup> Ohm
Comparative Tracking Index (CTI, tracking resistance)	DIN EN 60112 on FR 4 base material with CTI 275	CTI ≥ 600	CTI ≥ 600

Property	Test method	DSL 1602 FLZ/400	DSL 1602 FLZ/75
Resistance to condensation	based on ISO 6270-2 (BIAS 12 V, 40 °C [104 °F], 100% r. H.)	≥ 1.0 x 10 <sup>10</sup> Ohm no e-corrosion or migration	≥ 1.0 x 10 <sup>9</sup> Ohm no e-corrosion or migration
Permittivity ε <sub>r</sub>	Determination with a Balanced Circular Disk Resonator	67 GHz: ≈ 2.695 78 GHz: ≈ 2.735	not determined
	VDE 0303, part 4	100 kHz: ≈ 4.0 1 MHz: ≈ 3.7 1 GHz: ≈ 3.4	not determined
Dielectric loss factor tan δ	Determination with a Balanced Circular Disk Resonator	67 GHz: ≈ 0,012 78 GHz: ≈ 0,016	not determined
	VDE 0303, part 4	100 kHz: ≈ 0.0114 1 MHz: ≈ 0.016 1 GHz: ≈ 0.0432	not determined
TI (temperature index)	DIN EN 60216 (IEC 60216) issue 2001 20 000 h 5 000 h	132 °C [269.6 F]* 147 °C [296.6 F]*	138 °C [280.4 F]* 156 °C [312.8 F]*

\* can be used in a temperature range of **-65 to at least +130 °C [-85 to at least 266 °F]**. Both at the lower and upper ends of this range the performance and reliability of the material can be negatively affected in some applications. In such cases, additional pre-trials and tests are required. For determining the TI, a loss in mass of 50 % and/or 25 % of dielectric strength compared to the initial values has been fixed as a limit.

## Electrical properties immediately after UV curing

After UV curing, electrically insulating properties are already present; however, they may not yet reach the values stated above. Please consider this when performing functional tests directly after UV curing where the electrical values of the thick film coatings of the series **UV-LED Twin Cure® DSL 1602 FLZ** are demanded. The final properties are only achieved after about 8-14 days.

## Processing



Please read this technical report and the publications listed below carefully before using the product. These sheets are enclosed with the first shipment of product or sample

### MSDS

The corresponding material safety data sheet contains detailed information and characteristics on safety precautions, environmental protection, transport, storage, handling and waste disposal.

### AI

[Application information AI 1/1](#) "Processing instructions for ELPEGUARD® conformal coatings (thin film coatings)"

### TI

[Technical information TI 15/3](#) "Protective measures when using chemicals including lacquers, casting compounds, thinners, cleaning agents"

The thick film coatings of the series **UV-LED Twin-Cure® DSL 1602 FLZ** can be applied by automatic selective spray coating, by brushing or by means of dispensing.



Protect from UV light



Protect against humidity

Since the many different permutations make it impossible to evaluate the whole spectrum (parameters, reactions with materials used, chemical processes and machines) of processes and subsequent processes in all their variations, the parameters we recommend are to be viewed as guidelines only that were determined in laboratory conditions. We advise you to determine the exact process limitations within your production environment, in particular as regards compatibility with your specific follow-up processes, in order to ensure a stable fabrication process and products of the highest possible quality.

The specified product data is based upon standard processing conditions/test conditions of the mentioned norms and must be verified if necessary while observing suitable test conditions on processed products.

Feel free to contact our application technology department (ATD) if you have any questions or for a consultation.

### Auxiliary products recommended

- [ELPESPEC® cleaning agent R 5817](#) and reactive thinner VR 1600  
For cleaning work place and tools we recommend our cleaning agent **R 5817**. Clean equipment with **R 5817** and then rinse with reactive thinner **VR 1600**. Please see also our application information sheet **AI 1/2**, item “Cleaning equipment”.
- [ELPESPEC® cleaning agent R 5888](#)  
water-soluble, biodegradable cleaning agent for product carriers and tools
- [ELPEGUARD® Dam-and-Cure GEL 1602 FLZ-UV](#)  
Thixotropic dam material for the application of dams around connectors, components and contact surfaces as a boundary for subsequent conformal coating with UV (LED) curable systems.

### Drying/Curing

The curing process is based on two complementary chemical cross-linking mechanisms of different time lengths: UV LED curing and humidity curing.

UV LED curing with suitable lamps is mandatory. The specified final properties cannot be achieved by humidity curing alone.

The assemblies can already be packed or encapsulated 1-3 h after UV LED curing.

### UV LED curing

Curing is effected in UV LED curing units at a wavelength of 395 nm

→ Cure the **ELPEGUARD®** thick film coatings of the series **UV-LED Twin-Cure® DSL 1602 FLZ** as follows:

	Measuring device	Energy density (dose)	UV irradiance (intensity)
DSL 1602 FLZ/400	LED-Cure L395 von EIT / EIT2.0 LLC	2550 ± 500 mJ/cm <sup>2</sup>	2700 ± 500 mW/cm <sup>2</sup>
DSL 1602 FLZ/75	LED-Cure L395 von EIT / EIT2.0 LLC	5000 ± 500 mJ/cm <sup>2</sup>	5500 ± 500 mW/cm <sup>2</sup>

The LED-Cure L395 measuring device from EIT /EIT2.0 LLC is recommended. Upon request we will gladly provide the test report “Determination and measurement of the required curing energy for UV-LED curable protective coatings”.

The distance between lamp and assembly should be as low as possible.

## UV curing with mercury/gallium lamps

Curing can be effected in common UV curing units.

→ Determine the optimum energy level by performing pretrials.

The physical, mechanical and electrical properties reached after curing by means of mercury/gallium lamps may vary from the results listed above. For further information, you may refer to our test report DA 2019-296 provided upon request.

## Humidity curing

In shadow zones, the coating will cure by reacting with atmospheric humidity. Depending on the layout and assembly of the printed circuit board, this reaction is completed after 8-14 days. Only after this time the final properties are achieved.

## Packaging

The packing units available are indicated in our offer which we will send you upon request.

## Shelf life and storage conditions



Shelf life: In sealed original containers at least 6 months



Storage conditions: +5 °C to +25 °C [+41 °F to +77 °F]



Protect from UV light



Protect against humidity

For warehousing reasons, isolated cases may occur where the shelf life upon shipment is less than the shelf life indicated in this technical report. However, it is ensured that our products have **at least** two-thirds of their shelf life remaining when they leave our company. Labels on containers show shelf life and storage conditions.

## Disclaimer

All descriptions and images of our goods and products contained in our technical literature, catalogues, flyers, circular letters, advertisements, price lists, websites, data sheets and brochures, and in particular the information given in this literature are non-binding unless expressly stated otherwise in the Agreement. This shall also include the property rights of third parties if applicable.

The products are exclusively intended for the applications indicated in the corresponding technical data sheets. The advisory service does not exempt you from performing your own assessments, in particular as regards their suitability for the applications intended. The application, use and processing of our products and of the products manufactured by you based on the advice given by our Application Technology Department are beyond our control and thus entirely your responsibility. The sale of our products is effected in accordance with our current terms of sale and delivery.

Any questions? We would be pleased to offer you advice and assistance in solving your problems. Samples and technical literature are available upon request.